**PAT-NO:** JP405311144A

**DOCUMENT-IDENTIFIER:** JP 05311144 A

**TITLE:** HEAT-RESISTANT

**ADHESIVE** 

**PUBN-DATE:** November 22, 1993

## **INVENTOR-INFORMATION:**

NAME COUNTRY

INOUE, HIROSHI TAKABAYASHI, SEIICHIRO FUNAKOSHI, TSUTOMU SONOYAMA, KENJI

## **ASSIGNEE-INFORMATION:**

NAME COUNTRY

UBE IND LTD N/A

**APPL-NO:** JP04161599

**APPL-DATE:** May 12, 1992

**INT-CL (IPC):** C09J163/00, C09J179/08, C09J183/10

## **ABSTRACT:**

PURPOSE: To provide the adhesive having a specific

composition, capable of laminating a heat-resistant film to a copper foil at a low temperature to give a laminate containing the adhesive layer having sufficient adhesiveness and excellent flexibility and heat-resistance and, accordingly, suitable for the production of a flexible printed circuit board, etc.

CONSTITUTION: The adhesive contains (A) 100 pts.wt. of a soluble polyimide siloxane produced by reacting an aromatic tetracarboxylic acid component composed mainly of a biphenyltetracarboxylic acid compound (preferably 2,3,3',4'-biphenyltetracarboxylic acid dianhydride) with 10-80mol% of a diaminopolysiloxane of formula (R is bivalent hydrocarbon group; R1 to R4 are lower alkyl or phenyl; n is 3-60) and 20-90mol% of an aromatic diamine (preferably 1,3-diaminodiphenyl ether, etc.), (B) 1-60 pts.wt. of an epoxy.polyoxyalkylenemodified polysiloxane, (C) 15-250 pts.wt. of other epoxy compound, (D) 0.2-20 pts.wt. of an inorganic filler and (E) an epoxy hardener as resin components.

COPYRIGHT: (C)1993,JPO&Japio